

# panoRama One8020™



Self-Adhesive Outside Mount One-Way  
Vision Film - Available in 80/20  
Film/Hole Pattern

## APPLICATIONS

- Retail Windows & Building Wraps
- Event & Promotional Graphics
- Exterior Applications Up To 1 Year

[WWW.CGXUSA.COM](http://WWW.CGXUSA.COM)

CONTINENTAL  
GRAFIX

# panoRama One8020™

## MATERIAL

Face Film	Printable White Perforated Monomeric PVC
Backing	Black For Maximum Contrast
Adhesive	Removable Semi-Permanent Solvent Acrylic
Liner	Universal Paper Liner - 4mil
Thickness	6mil (145 microns)
FR Certification	ASTM E84, B1 & M1
Hole Diameter	1.5mm

## DURABILITY

Interior	Up To 3 Years
Exterior	Up To 1 Year - Vert. Exposure Under Norm. Cond.
Environment	Humidity & Solvent Resistance - Good
Shelf Life	12 Months
Storage Requirements	Store at +59°F to +68°F (+15°C to +20°C) with a Relative Humidity of 45% to 65%
Repositionable	No

## APPLICATION/REMOVAL

Application Temp	+50°F to +86°F (+10°C to +30°C)
Service Temp	+0°F to +122°F (-17°C to +50°C)
Removability	Cleanly Removable With No Adhesive Residue, Up To 6 Months - Adhesion May Increase Over Time
Removal Temp	+50°F (+10°C) Or Greater
Exclusions	NOT To Be Applied On Fresh Paint, Polycarbonate, And Some PVC (No Exhaustive List Available)

Surface must be clean and dry. Prevent contact with solvent or ammonia based cleaners. For best results, clean surface with a mild detergent and water and dry thoroughly. Always clean and dry surface prior to application.



### PRINTING METHODS

Digital - Solvent, Eco-Solvent, Latex & UV Inks; Screen Printing; Offset



### MATERIAL SIZES

60" x 656', 54" x 656', 60" x 164, 54" x 164', 60" x 50', 54" x 50'



### ADVANTAGES

- Economical Window Perf For Short Term Applications
- Universal Paper Liner For Easy Handling During Application
- Available with 1 Film/Hole Pattern One8020™ 80% Film/20% Hole

For additional product information, performance, and warranty guidelines please contact **Continental Grafix USA, Inc.** at 1.704.872.2216 or visit [www.cgxusa.com](http://www.cgxusa.com).

**Note:** For critical substrates, always test prior to application.